Appl. No. 10/062,095 Supplemental Reply to Office Action of June 20, 2003

This listing of claims will replace all prior versions, and llstings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A highly efficient fluorescent material from the class of the silicide nitrides having a cation and the basic formula $A_x Si_y N_z$, characterized in that the fluorescent material is [[$Sr_2 Si_5 N_8 Ce^{2*}$]] $Sr_2 Si_5 N_8 : Ce^{2*}$ or $Sr Si_y N_{10} : Ce^{3*}$.

2. (Cancelled)

- 3. (Original) The fluorescent material as claimed in claim 1, characterized in that the proportion of the Ce amounts to between 1 and 10 mol% of the Sr.
- 4. (Original) The fluorescent material as claimed in claim 1,
- 30 mol%, is replaced by Ba and/or Ca.

No. 2386 P. 3/5 From: CHICK

Appl. No. 10/062,095 Supplemental Reply to Office Action of June 20, 2003

- 5. (Previously Presented) A light source having a primary radiation source, which emits radiation in the shortwave region of the optical spectral region in the wavelength region of 370 of 430 nm, this radiation being converted wholly or partially into secondary radiation of longer wavelength in the visible spectral region by means of a first fluorescent material as claimed in claim 1.
- 6. (Original) The light source as claimed in claim 5, characterized in that a light-using diode based on InGaN is used as primary radiation source.

Appl. No. 10/062,095 Supplemental Reply to Office Action of June 20, 2003

- 7. (Original) The light source as claimed in claim 5, characterized in that a portion of the primary radiation continues to be converted into radiation of longer wavelength by means of a second fluorescent material, the first and second fluorescent materials being, in particular, suitably selected and mixed in order to generate white light.
- 8. (Original) The light source as claimed in claim 7, characterized in that a portion of the primary radiation continues to be converted into radiation of longer wavelength by means of a third fluorescent material, this third fluorescent material emitting in the red spectral region.